



Loctite® Frekote® PU7000™, PU7001™, PU7200™ Mold Release Agents and Sealers

Exceptional mold release performance on a variety of substrates, including polyurethanes.

- Easy to apply
- Fast curing
- Low mold buildup
- Minimal transfer
- Suitable for PU foam
- Designed for a variety of surfaces
 - Open cell foam
 - PU skin
 - Variety of finishes

Key applications include:

- Rigid PU Foam
 - Sporting equipment safety support pads (i.e., helmets)
 - Seating (i.e., amusement park, rail, agriculture)
 - Guards
- Elastomeric, Open Cell PU Foam
 - Pillows
 - Mattresses
- Thermoplastic Resins/Coatings/Films
 - Bowling pins
 - Golf carts



Call 1.800.LOCTITE (562.8483) for more information. To request a sample, visit www.henkelna.com/frekote



Loctite® Frekote® PU7000™, PU7001™, PU7200™ Mold Release Agents and Sealers

Frekote® PU release agents and sealers are designed as semipermanent release agents.



Loctite® Frekote® PU7000™

- Foam release
- Clear
- Gloss effect
- Very fast drying – 30 second cure at 110°F (43°C)
- Minimal transfer – more releases, less cleaning
- Solvent-based polymer
- Moisture cure
- Application temp: 95°F to 149°F (35°C to 65°C)
- Easy spray application
- Inert
- Thermally stable to 450°F (232°C)
- For flexible, resilient polyurethane foams with excellent open-cell or gloss surface

Available Sizes	
Item No.	Size
1664434	1 gal.
1664158	5 gal.
1666113	55 gal.

Loctite® Frekote® PU7001™

- Foam release
- Clear
- High slip
- Very fast drying – 30 second cure at 110°F (43°C)
- Low transfer – less part cleaning
- Solvent-based polymer
- Moisture cure
- Application temp: 95°F to 149°F (35°C to 65°C)
- Easy spray application
- Inert
- Thermally stable to 450°F (232°C)
- For flexible, resilient polyurethane foams, or semirigid PU foams

Available Sizes	
Item No.	Size
1669689	1 gal.
1670095	5 gal.
1670078	55 gal.

Loctite® Frekote® PU7200™

- Mold sealer/release
- Clear
- High slip
- Very fast drying – 30 second cure at 110°F (43°C)
- Minimal transfer – more releases, less cleaning
- Solvent-based polymer
- Moisture cure
- Application temp: 95°F to 149°F (35°C to 65°C)
- Easy spray application
- Inert
- Thermally stable to 450°F (232°C)
- For flexible, resilient polyurethane foams, or semirigid PU foams

Available Sizes	
Item No.	Size
1670058	1 gal.
1670077	5 gal.

U.S.A.

Henkel Corporation
Engineering Adhesives
One Henkel Way
Rocky Hill, Connecticut 06067
Tel: 1.800.LOCTITE (562.8483)
Tel: 860.571.5100
Fax: 860.571.5465

Canada

Henkel Canada Corporation
Engineering Adhesives
2515 Meadowpine Blvd.
Mississauga, Ontario, L5N 6C3
Tel: 1.800.263.5043 (*within Canada*)
Tel: 905.814.6511
Fax: 905.814.5391

www.henkelna.com/frekote

